



TECHNICAL DATA SHEET

ZNO GRADE 500H

Description

ZNO Grade 500H is manufactured by French (Indirect) Process with slightly higher surface area, high assay and low impurities. ZNO Grade 500H meets the requirements of ASTM specification D79 for paint, EC RoHS for heavy metal limits, and End of Live Vehicles (ELV Directive), and other regulations where good quality zinc oxide is required.

ZNO Grade 500H is also available in pelleted form (ZNO Grade 500HP) and with processing aid treatment additive (ZNO Grade 500H-T).

Uses

This grade is used where lower impurities are required and increased zinc oxide reactivity provides benefits in the application, such as certain zinc chemicals may require less reactor time, or the end product may have improved clarity or color.

TYPICAL CHEMICAL PROPERTIES

Chemical Analysis (%)	Typical Limit*	Nominal	Test Method
ZnO (Zinc Oxide) dry basis	99.8 min.	99.9	Supplier
Pb (Lead)	0.03 max.	0.01	ASTM D4075
Cd (Cadmium)	0.01 max.	0.005	ASTM D4075
Fe (Iron)	0.006 max.	0.002	ASTM D4075
Loss at 110°C (Moisture)	0.35 max.	0.2	ASTM D280

TYPICAL PHYSICAL PROPERTIES

Surface Area (m ² /g)	6.0 - 8.5	7	ASTM D4315
Fineness retained on 325 mesh (%)	0.02 max.	0.01	ASTM D4315
(Fineness passing 325 mesh (%))	99.98 min.	99.99	ASTM D4315

Standard Packaging: 50 lb. net wt. Kraft bags, 48X40 2-way wood pallets 2,000 lb net wt.

Customer specifications supersede above limits. Zinc Oxide LLC (ZNO) can produce zinc oxide to meet specific customer specifications or application requirements. *Two sigma μ (>98%).

For additional information, contact : Ed Smith, Vice President - Sales, email: ed.smith@zn-oxide.com, Office +1 615 446 8791

